



Efficiency of Shell Waste as a Source of Calcium Carbonate to Produce Calcium Oxide through Calcination Process

Nya Daniaty Malau ^{a*} and Manogari Sianturi ^a

^a Department of Physics Education, Universitas Kristen Indonesia, Indonesia.

Authors' contributions

This work was carried out in collaboration between both authors. Both authors read and approved the final manuscript.

Article Information

DOI: 10.9734/AJARR/2024/v18i5644

Open Peer Review History:

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://www.sdiarticle5.com/review-history/115178>

Original Research Article

Received: 25/01/2024
Accepted: 29/03/2024
Published: 02/04/2024

ABSTRACT

Aims: The aim of this research is to examine the efficiency of batik shellfish shells as a source of calcium carbonate to produce calcium oxide compounds.

Study Design: The type of research is Experimental.

Place and Duration of Study: Sample: Department of Physics Education, Kristen Indonesia University, Jakarta, between June 2023 and December 2023.

Methodology: There are two stages in the research process, namely the first stage is the preparation and sterilization of batik shellfish shells. The second stage is the calcination of batik shellfish shells to produce CaO. Clean the batik shellfish shells using distilled water. Then crush them using a hammer until they become small fragments. Next, dry the small fragments of batik shellfish shells by air-drying them in a closed room. Then, the sample inside the container will undergo calcination process using a furnace/heating furnace with temperature variations of 800°C and 900°C for 8 hours.

*Corresponding author: Email: malaunyadaniaty@gmail.com;

Results: The results obtained show the formation of CaO compounds with the characteristic white color of CaO powder and small or fine particle size. The average efficiency of CaO compounds resulting from the calcination of batik shellfish shells at a temperature of 800°C is 61.85%. Meanwhile, the average efficiency of CaO compounds resulting from the calcination of batik shellfish shells at a temperature of 900°C is 55.64%.

Conclusion: The average efficiency of CaO compounds resulting from the calcination of batik shellfish shells at 800°C is greater than the average efficiency of CaO compounds obtained at a calcination temperature of 900°C. This is because the higher the temperature, the purer the CaO compounds produced will be. Therefore, the CaO compound produced from calcination at a temperature of 900°C can be utilized as a source of calcium in various fields.

Keywords: Calcination; shell; batik shellfish; CaO.

1. INTRODUCTION

Indonesia is rich in abundant aquatic resources, one of which is shellfish. In Indonesian waters, there are thousands of species of shellfish, some of which have high economic value, such as green mussels, blood cockles, pearl oysters, razor clams, and oysters. Additionally, there is also batik shellfish which has recently gained popularity among the community. Indonesian society has not fully utilized the potential of the abundance of shellfish. Generally, people consume the meat and discard the shell of shellfish. Based on previous research, these unused shellfish shells can cause environmental problems, especially regarding cleanliness [1]. Various types of shellfish are often only used as food because of their high protein content, while their shells are used as ornaments or decorations [2]. Currently, shells are only utilized in handicrafts, such as decorations or as additives in animal feed [3].

The batik shellfish is a favorite among local communities because of its delicious meat. The taxonomy of the batik shellfish (*Paphia undulate*) is as follows: Phylum Mollusca, class Bivalvia, Order Veneroida, Genus *Paphia*, and Species *Paphia undulate*. This shellfish has an elongated elliptical shell, with a greenish-brown color and dark brown zigzag pattern decorations. The shell is somewhat thick and yellowish-brown, with a smooth and shiny surface [4].

Shellfish shells contain more calcium than shellfish meat [5], but they have not been fully utilized yet. Previous research has found that the main component of shellfish shells is calcium carbonate (CaCO_3) at around 96% [6]. Additionally, there is other research stating that the composition of shellfish shells is 98% calcium carbonate, 0.79% MgCO_3 compound, and 0.15% SrCO_3 compound.

Some methods used for calcium extraction from shellfish shells include carbonation [7], deproteinization [8], and calcination [9]. Among these three methods, the easiest and most effective in producing high-quality calcium is the calcination method (heating at high temperatures). If calcium carbonate from shellfish shells is heated to temperatures above 700 °C, it will transform into calcium oxide (CaO) [10]. Besides high temperature, the heating time also affects the characteristics of the resulting CaO compound [11]. If the heating temperature of the shellfish shells is raised to 750 °C to 800 °C, the obtained CaO compound will have better characteristics compared to at 700 °C. High temperature is necessary to heat the shellfish shells so that the water content, organic compounds, and carbon dioxide within the shellfish shells are removed, and the expected compound present is pure CaO.

From several previous studies, it has been found that the utilization of shellfish shell waste is still not optimal, especially as a source of calcium carbonate (CaCO_3) which can then produce solid CaO compounds through high-temperature heating processes, and with appropriate treatment, CaO derived from shellfish shell waste can be used for various purposes in daily life. The aim of this study is to examine the efficiency of batik shellfish shells as a source of calcium carbonate to produce calcium oxide compounds. It is hoped that the produced CaO can be used as an environmentally friendly material and can be widely applied in various fields.

2. METHODS

There are two stages in the research process, namely the first stage is the preparation and sterilization of batik shellfish shells. The second stage is the calcination of batik shellfish shells to

produce CaO. In the Sample Preparation and Sterilization stage, it begins with the collection of batik shellfish shells to be used. The batik shellfish shells used are household waste from the Kalimantan region. Prepare 0.5 kg of batik shellfish shells. Clean the batik shellfish shells using distilled water. Then crush them using a hammer until they become small fragments. Next, dry the small fragments of batik shellfish shells by air-drying them in a closed room. This is to prevent contamination of the samples by impurities if they were to be dried outdoors.

The drying process is carried out for 24 hours. If the sample is already dry, it can proceed to the next stage, namely the sample calcination. Batik shellfish shells prepared in the previous stage are weighed before being placed into a

container/crucible. Then, the sample inside the container will undergo calcination process using a furnace/heating furnace with temperature variations of 800°C and 900°C for 8 hours. Afterward, the sample is cooled. Next, the resulting calcination in the form of CaO, batik shellfish shells are crushed using a mortar, placed into sample plastic bags, labeled with their names, and then weighed to determine their mass.

Information:

1. Batik shellfish shell sample
2. Prepared sample
3. Sample weighed
4. Sample calcined
5. Sample crushed with a mortar
6. CaO powder




Fig. 1. Steps of calcination of batik shellfish shells

3. RESULTS AND DISCUSSION

The results of the calcination of batik shellfish shells using a furnace with temperature variations of 800°C and 900°C, each for 8 hours, are in the form of powder as shown in Fig. 2. From the three repetitions conducted and observed, there is a significant difference in the color of the samples before and after calcination. The initial milk chocolate color of the sample turns white after calcination.

This is evident in both samples that were calcined at temperatures of 800°C and 900°C. This means that at both calcination temperatures of 800°C and 900°C, the batik shellfish shell samples have produced CaO compounds. This is consistent with previous research stating that shellfish shells heated at temperatures above 700°C will transform into CaO compounds [10]. Additionally, the change in color to white is an indicator of the transformation of the compound found in limestone, which was initially CaCO₃ and has now changed to CaO [12].

The compound which was initially CaCO₃ then decomposes into CaO through calcination temperatures of 800°C and 900°C. This decomposition occurs due to a high-temperature

combustion process, resulting in the release of carbon. Below is the reaction of the decomposition of CaCO₃ compound into CaO compound.



When comparing the most effective calcination temperature in producing CaO compounds, it is found that 900°C is the optimal temperature. This is because the higher the calcination temperature, the purer the CaO compound obtained.

From Table 1, the average efficiency of CaO compound resulting from the calcination of batik shellfish shells at 800°C is 61.85%. Meanwhile, from Table 2, it can be observed that the average efficiency of CaO compound resulting from the calcination of batik shellfish shells at 900°C is 55.64%. Comparing the average efficiency of CaO compound resulting from calcination at 800°C and 900°C, it can be seen that the average efficiency of CaO compound obtained at a calcination temperature of 800°C is higher than that obtained at a calcination temperature of 900°C. This is because the higher the temperature, the purer the CaO compound produced.



Fig. 2. Powder resulting from the 8-hour calcination of batik shellfish shells. (a) At a temperature of 800°C. (b) At a temperature of 900°C

Table 1. Efficiency of CaO compound from the calcination of batik shellfish shells at 800°C temperature

Batik Shellfish Shell Samples	Mass		Efficiency
	Before Calcination (CaCO ₃)	After Calcination (CaO)	
Container 1	21, 74 gram	13,98 gram	64,3 %
Container 2	24, 79 gram	11,99 gram	48,3 %
Container 3	27,05 gram	18,86 gram	69,7 %
Container 4	30,87 gram	20,09 gram	65,1 %
Average Efficiency			61,85 %

Table 2. Efficiency of CaO compound from the calcination of batik shellfish shells at 900°C temperature

Batik Shellfish Shell Samples	Mass		Efficiency
	Before Calcination (CaCO ₃)	After Calcination (CaO)	
Container 1	43,79 gram	24,33 gram	55,56 %
Container 2	47,09 gram	26,24 gram	55,72 %
Average Efficiency			55,64 %

When heating is conducted at a higher temperature, the water content, organic compounds, and carbon dioxide present in the shellfish shells are lost, and the expected compound to form is pure CaO. The difference in average efficiency values at 800°C and 900°C is not significantly different, only about $\pm 6\%$, so if it is not possible to raise the calcination temperature to 900°C, using a calcination temperature of 800°C can still be considered. However, at 800°C, there may still be some impurity compounds present. But if 900°C is feasible, the resulting CaO compound will be purer.

In Table 1, there is a significant difference in the efficiency values of the CaO compound produced between containers 1, 3, and 4 compared to container 2. Containers 1, 3, and 4 have average efficiency values above 60%, while for container 2, the average efficiency value of the CaO compound produced is 48%. This is because during the calcination process, container 2 broke inside the furnace, causing some of the batik shellfish shell samples to fall out of the container. The weighed sample is only the portion that remained inside container 2, resulting in a different efficiency value of the CaO compound produced compared to containers 1, 3, and 4. However, when calculating the average efficiency values of the CaO compound produced across containers 1 through 4, the obtained results are still above 60%.

4. CONCLUSION

The batik shellfish shells were successfully calcined into CaO at temperatures of 800°C and 900°C with a calcination time of 8 hours. The results obtained include the formation of CaO compounds with characteristic white CaO powder color and small or fine particle size. The average efficiency of the CaO compound resulting from the calcination of batik shellfish shells at 800°C is 61.85%. Meanwhile, the average efficiency of the CaO compound resulting from the calcination of batik shellfish shells at 900°C is 55.64%. The average

efficiency of the CaO compound resulting from the calcination of batik shellfish shells at 800°C is higher than the average efficiency of the CaO compound obtained at a calcination temperature of 900°C. This is because the higher the temperature, the purer the CaO compound produced. When heating is conducted at a higher temperature, the water content, organic compounds, and carbon dioxide present in the shellfish shells are lost, and the expected compound to form is pure CaO.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

REFERENCES

- Fitriah E, Maryuningsih Y, Roviati E. Utilization of green mussel meat and shells (*Perna viridis*) as processed foods high in calcium. Proceeding of The Urecol. 2018; 412-423.
- Samson E dan, Kasale D. Diversity and abundance of bivalves in the coastal waters of Waemulang, South Buru District. Journal of Tropical Biology. 2020;20(1): 78-86.
- Ahmad I. Utilization of blood clam shell waste (*Anadara granosa*) as an abrasive in toothpaste. Galung, Tropika Journal. 2017; 6(1):49-59.
- Nurkhasanah D, ElinahE, Nugraha EH. Morphometric analysis and condition index of batik shells (*Paphia undulate*) in Cirebon waters. Journal of Fisheries and Marine Technology. 2021;11(2):183-188. Available:https://doi.org/10.24319/jtpk.11.1 83-188
- Cho MG, Bae SM, Jeong JY. Egg shell and oyster shell powder as alternatives for synthetic phosphate: Effects on the Quality of Cooked Ground Pork Products, Korean J. Food Sci. Anim. Resour. 2017;37(4): 571-578.
- Yoon GL, Kim BT, Kim BO, Han SH. Chemical-mechanical characteristics of

- crushed oyster-shell. Waste Manag. 2003; 23:825–834.
Available:https:// doi.org/10.1016/S0956–053X(02)00159–9
7. Lee SM, Lee SH, Jeong SK, Youn MH, Nguyen DD, Chang SW, Kim SS. Calcium extraction from steelmaking slag and production of precipitated calcium carbonate from calcium oxide for carbon dioxide fixation. J. Industrial and Engineering Chem. 2017;53:233-240.
 8. Firdaus S, Cahyati AI, Nastiti RWD, Aminah S. The potential of serimping shellfish waste as a source of calcium for bone density maintenance. Agriscientics Journal of Agricultural Sciences. 2018; 2(2): 108-112.
 9. Hariyati Shofiyani A, Wibowo MA. Extraction of Calcium Carbonate (CaCO₃) from Ale-Ale Shell Base Material (*Meretrix meretrix*) at Calcining Temperature 500°C, Journal of Equatorial Chemistry. 2019; 8(1):54-58.
 10. Sirisomboonchai S, Abuduwayiti M, Guan G, Samart C, Abliz S, Hao X, Kusakabe K, Abudula A. Biodiesel production from waste cooking oil using calcined scallop shell as catalyst. Energy Convers. Manag. 2015;95:242–247.
DOI: 10.1016/j.enconman.2015.02.044
 11. Ramasamy KK, Gray M, Job H, Santosa D, Li XS, Devaraj A, Karkamkar A, Wang Y. Role of calcination temperature on the hydrotalcite derived MgO-Al₂O₃ in converting ethanol to butanol. Top. Catal. 2016;59:46–54.
Available:https://doi.org/10.1007/s11244–015–0504–8
 12. Malau Nya Daniaty, Adinugraha Fajar. Determination of CaO optimum calcining temperature of duck eggshells and quail eggshells. Journal of Edu Mat Sains. 2020;4(2):193-202.

© Copyright (2024): Author(s). The licensee is the journal publisher. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:
The peer review history for this paper can be accessed here:
<https://www.sdiarticle5.com/review-history/115178>